




# FIBRIMAT F450

## Technical Datasheet



PRODUCT DESCRIPTION	
Reinforcement type	Nonwoven
Process	Carding / Cross-lapping / Needlepunching
Fiber type	Flax
Packaging	Rolls: 15m x 1m

TECHNICAL DATA		
Data	Unit	Value
Areal weight	g/m <sup>2</sup>	450 (± 10 %)
Thickness	mm	4 (± 1)
Molded thickness (single layer) <i>at -500 mbar</i>	mm	1.7 (± 0.1)

RECOMMENDATIONS FOR USE	
Molding process	Liquid Composite Molding process (RTM, RTM light, Infusion,...)
Reinforcement drapping	Preferential fiber direction : roll axis
Storage	Store in a dry area

### Contact:

Guilherme Apolinario Testoni  
Development & Technical Sales

*Tel:* +33 2 32 70 42 20

*Email:* [guilherme@eco-technilin.com](mailto:guilherme@eco-technilin.com)