

Advantages

- Low cost system ideal for all size moulds
- Epoxy and polyester compatible
- High dimensional stability
- Long-life moulds
- Highly polishable hard-wearing surface
- No special equipment or processing

Uni-Mould™ Advantages

Traditionally, moulds made using polyester resin and gel coat are unsuitable for use as moulds for epoxy-based parts due to well-known release problems when used in this combination. Most polyester moulds also suffer from distortion (pulling), particularly on larger moulds, and cannot be used at elevated temperatures, making them unsuitable for in-mould post-curing.

Uni-Mould is different. It features unique vinylester chemistry which is 100% compatible with epoxy, vinylester, polyester and pre-pregs making it a genuinely universal tooling system. Its specially formulated resin systems are designed to be dimensionally stable up to the Maximum Service Temperature of 90°C and will not pull as they cure resulting in more dimensionally accurate moulds.

Moulds made using Uni-Mould are highly polishable and, in combination with a chemical release agent (such as Easy-Lease), will result in high-gloss parts straight out of the mould, time after time.

Uni-Mould is designed to be used with low-cost emulsion bound glass chopped strand mat (CSM) reinforcement which breaks down excellently in the resin, just like it would with a polyester resin, meaning that it is an ideal and cost-effective way to create medium to large moulds.

Use with Prepregs

Although it is possible to use Uni-Mould moulds with out-of-autoclave (oven cure) prepregs (such as XPREG® XC110) we no longer recommend Uni-Mould moulds for this purpose.

Instead – for prepreg use – better results will be achieved using high temperature epoxy moulds made using our EG160 / EMP160 tooling system or XPREG® XT135 Tooling Prepreg. These high temperature epoxy tooling systems allow the prepreg to be cured at the optimum 120°C which reduces the cure time and improves the mechanical properties of the component. Additionally, epoxy tools have been found to result in a better surface finish with prepregs such as XPREG® XC110.

The Uni-Mould™ System

The Uni-Mould system is made up of 3 specially formulated resins, all capable of high operating temperatures and filled for zero shrinkage:

UG1 Uni-Mould Tooling Gel Coat (single /double application to 0.8mm)

UC1 Uni-Mould Coupling Coat (used with 1 layer of 150g CSM)

UT1 Uni-Mould Tooling Resin (used with 4 layers of 450g CSM)

Application Guide

This step-by-step application guide assumes that your pattern or master is made from a suitable material, is fully cured, sealed and prepared with a suitable release agent.

The guide assumes a mould of 1-2sqm. For larger moulds (up to the size of full boat hulls) the Uni-Mould system is still ideal but special measures need to be undertaken when applying the mould reinforcement. Please contact us for more details.

UG1 Uni-Mould Tooling Gel Coat Application



UG1 Uni-Mould Tooling Gel Coat should be catalysed at 1.5-2% using standard MEKP catalyst. Before application allow the catalysed gel coat to stand for a few minutes to settle and de-gas.

Gel coat should be applied in two applications. For the first application aim for a consistent thickness of 0.3–0.4mm. Allow the first application to cure for around 2-3hrs (at 20°C room temperature)

before applying the second coat of gel coat, again aiming for a thickness of 0.3 - 0.4mm.

Allow the gel coat to cure for a minimum of 4hrs (at 20°C room temperature), preferably overnight..

UC1 Uni-Mould Coupling Coat Application



The UC1 Uni-Mould Coupling Coat is designed to eliminate print-through of the mould reinforcement, to reduce the risk of blisters underneath the gel coat by ensuring the gel is reinforced with a skin of resin and glass and to provide an ideal substrate for the main reinforcement.

UC1 Uni-Mould Coupling Coat should be catalysed with standard MEKP at 1.5 – 2%. Apply a layer of the coupling coat over the mould surface and then add a single layer of 150g CSM. We do not recommend the use of glass surface tissue in lieu of the 150gsm CSM.

Wet out the CSM thoroughly with the coupling coat resin and ensure that all air is removed from the reinforcement, that it is well wetted through and that the reinforcement is conforming to all the contours of the mould, particularly any tight corners.

UT1 Uni-Mould Tooling Resin Application



The laminating technique for the UT1 Uni-Mould Tooling Resin is quite different from conventional polyester laminating resins and it is essential that you familiarise yourself with this technique and follow the guidelines carefully in order for the resin to cure properly and result in a successful mould.

UT1 Uni-Mould Tooling Resin is cured by its own exotherm and must reach a temperature of 50-60°C during its cure in order to achieve its full properties. In order for this to happen your workshop environment needs to be between 18°C and 25°C and you must lay down a minimum of 4 layers of 450gsm or resin-rich (4:1) CSM onto the back of the mould in a single session.

Preparation

In order to ensure that all the reinforcement can be laid down in a single session it is important to prepare the resin and reinforcement in advance before starting to laminate.

Cut your 450gsm CSM to the right shapes for your mould, allowing for a minimum of 4 layers of mat. Once you have cut the mat, weigh it to see how much CSM you will be using.

Next, weigh out 4 times the weight of the glass in resin (UT1 Uni-Mould Tooling Resin should be used at a typical 4:1 ratio or resin to glass) which means if you are using 5kgs of CSM to reinforce your mould you should prepare 20kgs of resin.

Begin Laminating

When you are ready, catalyse the resin using MEKP catalyst at 0.75 – 1.25% (depending on the ambient temperature) and mix thoroughly.

Working quickly, apply resin all over the mould and then add layers of glass one at a time, wetting with plenty of resin (4:1 by weight) until you have added all the layers of glass to the back of the mould. You should use the last of the prepared resin as you add the last layer of CSM.

As the laminate starts to cure the temperature will rise to 50-60°C and the colour of the laminate will change from a mid brown to a light brown colour.

Allow the resin to cure fully for 24hrs.

Post Curing

For ambient temperature use, a post cure of the mould is recommended, but not required. If you intend to use the mould for higher temperature curing or in-mould post curing of your parts then an elevated temperature post cure is required.

Recommended post-cure for elevated temperature mould use:

10hrs at 60°C > 2hrs at 70°C > 2hrs at 80°C > 2hrs at 90°C

Finished Use

Composite moulds made from the Uni-Mould system can be used for wet-lay, vacuum bagging and resin infusion. Moulds made from Uni-Mould are 100% compatible with epoxy resin, polyester resin and vinylester resin.

Polishing



Moulds made using Uni-Mould are highly polishable to a full gloss and can easily be restored if they are subject to light scratches using a composites polishing compound (such as Mirka T10). After polishing, ensure a thorough re-application of release agent before use.

Release Agent

Because Uni-Mould's tooling gel coat is fully compatible with epoxy, polyester and vinylester, a wide range of release agents (waxes and chemical release agents) should all result in a good release. Uni-Mould is tested and recommended for use with Easy-Lease Chemical Release Agent which is universally suitable for all resin systems and processes.

Disclaimer

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

Our technical advice, whether verbal or in writing, is given in good faith but Easy Composites Ltd gives no warranty; express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product for their particular application and circumstances.

Easy Composites Ltd shall be in no way responsible for the proper use and service of the product, nor for the safeguarding of personnel or property, all of which is the duty of the user. Any information or suggestions are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.

Before using any of our products, users should familiarise themselves with the relevant Technical and MSDS provided by Easy Composites Ltd.

Easy Composites Ltd

Unit 39, Park Hall Business Village, Longton, Stoke on Trent, Staffordshire, ST3 5XA, United Kingdom.

Tel. +44 (0)1782 454499, Fax. +44 (0)1782 596868, Email sales@easycomposites.co.uk, Web www.easycomposites.co.uk